



CULP

DATE: OCTOBER 26, 2017

PATTERN: MOTO

FIBER CONTENT:	(Fabric) 80%POLYE20%ACR	
CONSTRUCTION:	25 Picks Per Inch 38 Ends Per Inch	
WIDTH:	54"	
WEIGHT:	Approx. 1.357 lbs. per linear yard	
*COLORFASTNESS CODE:	"W"	
SEAM BREAKING STRENGTH: (ASTM D-4034)	Warp/Filling	91/83
TEAR STRENGTH:	Warp/Filling	58/47
SEAM SLIPPAGE: (ASTM D-4034)	Warp/Filling	43/41
TENSILE STRENGTH: (ASTM D-5034)	Warp/Filling	224/148
ABRASION: (ASTM D-4157)	Medium Duty – 12,000 Cycles (Wyzenbeck - Wire Screen Abradant)	
PILLING: (ASTM D-3511)	Class 3	
UFAC:	Class I	
CALIFORNIA TECHNICAL BULLETIN 117-2013	Pass	
COLORFASTNESS TO LIGHT: (ASTM D-3597, AATCC-16A)	40 Hours - Class 4	
COLORFASTNESS TO CROCKING: (ASTM D-3597, AATCC-8)	Dry - Class 4.5 Wet - Class 4.0	
DYNAMIC SEAM FATIGUE: (ASTM D-4033)	Pass 5,000 Cycles	
FABRIC GRADE:	B	
THEORETICAL PATTERN REPEAT:	WARP N/A"	FILL N/A"

- * "Spot clean only with water based shampoo or foam upholstery cleaner. Pretest a small, inconspicuous area before proceeding. Do not overwet. Do not use solvents to spot clean. Pile fabrics may require brushing with a non-metallic, stiff bristle brush to restore appearance. Hot water extraction or steam cleaning is not a recommended cleaning method. Cushion covers should not be removed and laundered. To prevent overall soiling, frequent vacuuming or light brushing with a non-metallic, stiff bristle brush to remove dust and grime is recommended. When cleaning a spill, blot immediately to remove spilled material. Clean spots or stains from the outside to the middle of the affected area to prevent circling. Use a professional furniture cleaning service when an overall soiled condition has been reached."