



VIP - VALDESE INTERNATIONAL PRODUCTS

SPEC SHEET

P.O Box 70 - Valdese, North Carolina 28690
Phone (828)874-2181

Date: 03/17/2023

Material: I-76725
Material Name: UV SANDBERG-BARK
Content: 100.00% UV SOL DYE

Railroaded: Yes

Finished Pks/Inch: 046 Ends/Inch: 000 Country of Origin: China
Inherent Finish: (C-ZERO, ANTIMICROBIAL SBR BACKING IMPORT)
Unfinished Width: 0.000 Appx Finished Width: 56.264
Horizontal Repeat: 0.000 Vertical Repeat: 0.000
OZ/Linear YD: 12.912 OZ/SQ YD: 8.262
LBS/Linear YD: 0.81 G/M2: 280.14
Method of Repeat: STRAIGHT Tariff Code: 5906.99.2500
Flame Resistance:

Class I UFAC Class
Pass California TB 117-2013
Large Scale 701 QM Test
Small Scale 701 QM Test
Motor Vehicle Safety Std 302
Other (Specify)

Cleaning Code W/S/*B - *Diluted Bleach 10:1

Surface Abrasion: 63,000 Test Method: Duck Cloth
Surface Abrasion: Test Method: WIRE
ASTM D4157-02 Light Duty 3,000 cycles (double rubs) min.
Medium Duty 9,000 cycles (double rubs) min.
Heavy Duty 15,000 cycles (double rubs) min.
Contract Heavy Duty 30,000 cycles (double rubs) min.
Test Method

Martindale 45,000

Table with 4 columns: PERFORMANCE CHARACTERISTICS, STANDARD REQUIREMENTS, TEST RESULTS, and values. Rows include Resistance to Slippage, DSF Grade, Tear Strength, Break Strength, Elongation, Pilling, Colorfastness to Light, Crocking, and Water/Solvents.

Comments: