

Architectural Specifications

1.1 Product Description

1.1.1	k® products are made with high density polyurethane with an overall density similar to white pine at 13 to 17 pounds per cubic foot. The urethane process provides a greater skin density than core density for increased durability.
1.1.2	All products are manufactured with a white or semi-white color coating. Further, these products receive a primer coat finish before they are shipped to customers. The combination of the integral shell-like skin, the barrier coat, and the primer top coat provide an excellent substrate for durable finishes.
1.1.3	Ultra violet rays do not affect properly coated products.
1.1.4	The compressive strength of polyurethane products falls within the 300-400 P.S.I. range. (The parts are not intended for structural use).
1.1.5	The tensile strength of polyurethane products falls within the 350-400 P.S.I. range. (The parts are not intended for structural use.)
1.1.6	The degree of flexibility of any given polyurethane product is determined by the size and shape of its cross section.
1.1.7	urethane has a closed cell structure which provides protection from most solvents and renders it almost completely hydrophobic. It will not rot.
1.1.8	All urethane products resist the growth of mildew and fungus and further provide no nutritional value for other organisms such as small rodents.

1.2 Submittals

1.2.1	Submit urethane product data and shop drawings for customer approval.
-------	---

2.1 Acceptable Manufacturer

3.1 Installation

3.1.1	Inc. urethane products are handled in the same manner as wood millwork.
3.1.2	adhesives refer to model PL Premium.
3.1.3	Fasteners refer to nails, screws, bolts etc.
3.1.4	adhesives and fasteners must be used for installing all products on concrete, metal, vinyl or wood. Adhesive must be used on all joints to ensure the beauty of your installation for years to come.

Architectural Specifications

3.2 Finishing

3.2.1 Millwork, Inc. products are supplied with a white or beige primer base coat, ready for finishing top coat. A good quality exterior or latex or oil base paint may be used on rigid Inc. product. The surface must be clean, dry, and free from all greases or waxes before all finish work is begun.

3.3 Warranty

3.3.1 Inc. warrants its urethane product upon the following conditions against defects in materials and workmanship for the product's lifetime when used and installed under recommended conditions. Purchaser and installer must inspect each piece prior to installation. Both parties waive all defects which could have been discovered by reasonable inspection prior to installation.

3.3.2 Warranty will automatically be void if installation methods are not used as per section on Installation.

3.3.3 In the event claim is made under this warrant, has the right to inspect the part and determine at their discretion, that the parts supplied are defective. will repair, or if necessary, replace the defective parts if returned freight prepaid to place of manufacturing. If determines the parts cannot be repaired or replaced, will refund to the distributor the amount paid to for the said defective parts.

3.3.4 shall have no liability to any person, firm or corporation whatsoever for incidental or consequential damages such as but not limited to, labor, finishing, parts damaged by freight carriers, freight charges, installation, lost profits, and lost sales or the like.

3.3.5 No purchaser may take any deduction or credit against any amount owed to or make any charge back without the expressed written consent of

3.3.6 No purchaser may take any deduction or credit against any amount owed to or make any charge back without the expressed written consent of

MSDS

Section 1 General Product & Company Information

Chemical Name Foamed Polyurethane

Section 2 Hazardous Ingredients

Hazards None Known

Section 3 Physical / Chemical Characteristics

Density 5 - 42 lbs per cubic foot
Boiling Point N/A Material is Solid
Vapor Pressure N/A Material is Solid
Melting Point Vapor N/A
Density N/A
Evaporation Rate N/A
Appearance Exterior - White, Off-White, or Yellow
Interior - White or Yellow
Odor None

Section 4 Fire & Explosion Hazard Data

Flash Point N/A
Extinguishing Method Dry Chemical, CO₂, Foam, or Water
Special Firefighting Procedures Wear approved self-contained breathing apparatus
Unusual Fire & Explosion Hazard N/A

Section 5 Reactivity Data

Stability Stable - Yes
Unstable - No
Conditions to Avoid Avoid an open flame
Hazardous Decomposition Products Combustion may form CO, CO₂, Benzene, Nitrogen Oxides, and/
or Hydrogen Cyanide.
Hazardous Polymerization None will occur

Section 6 Health Hazard Data

Acute	Cutting, Grinding, or Sanding polyurethane foam can generate dust. This dust may cause respiratory irritation if inhaled.
Routes of Entry	
Skin	Possible
Ingestion	Possible
Threshold Limit Value (TLV)	None Established
Chronic	None Known
Signs/Symptoms of Exposure	Eye and/or respiratory tract irritation. Redness and/or swelling on areas of contact.
Emergency/First Aid	
Inhalation	Remove from area if dust is inhaled. Consult physician if irritation continues.
Eye Contact	Flush eyes with water. Consult physician if irritation continues.

Section 7 Precautions for Safe Handling and Disposal:

Waste Disposal Method:	Disposal in accordance with local, state, and federal regulations for disposal of solid waste.
Special Precautions:	Store in a temperature-controlled environment away from extreme heat, cold, and flame or possible.
Steps to be taken if material is released or spilled	N/A

Section 8 Control Measures

Respiratory Protection:	No Respirator necessary.
Ventilation:	Adequate ventilation when cutting or sanding is required.
Protective Gloves:	Not necessary, but suggested.
Eye Protection:	Safety glasses with eye shields when cutting or moving.
Other Protective Clothing or Equipment:	Eye wash station should be available.

NOTE: All information in this document is believe to be accurate as of 8/1/2010