

TECHNICAL SPECIFICATIONS

Test Standards			
Test Items	National Quality test Standards of Top Quality Production	Testing Result	Remarks
Water Absorption, %	$E \leq 0.5$	0.21	Pass
MOHS, Mpa	≥ 35	53	Pass
The quality of tile surface	There are no defects on the surface of 95% tiles.	No defect on the surface of tiles	Pass
Length (Width) mm	307.0 ± 1.5	307.0~307.6	Pass
Thickness, mm	7.7 ± 0.38	7.6~7.8	Pass
Side bending %	± 0.5	-0.06~0.11	Pass
Center bending %	± 0.5	-0.05~0.10	Pass
Side Straight %	± 0.5	0~0.03	Pass
Right Angle %	± 0.6	-0.11~0.20	Pass
Chemical Resistance	Put them in 3% HCL solution, 96h divided	GLA	Pass
	Put them in 30g/LKOH solution, 96h divided	GLA	

WalkOn Tile

12353 Wilshire Boulevard
 West Los Angeles, California 90025
 t. 310.442.1008 中文專線 310.494.1351
 f. 310.442.1028