



DATA SHEET / SPECIFICATION

CH 3532

Description:

Combustion modified polyurethane foam.

CH 3532		
Property	Test Procedure	CH 3532
Relative Net Density	ISO 845	33.25-38.5 kg/m ³
Hardness ILD (40%)	ISO 2439	98.4-141.6 N
SAG Factor	ISO 2439	Min 2.3
Compression Set (50% 22h 70°C)	ISO 1856	Max 9 %
Resilience	ISO 8307	Min 45 %
Tensile Strength	ISO 1798	Min 70 kPa
Elongation at Break	ISO 1798	Min 80 %
Flammability	BS 5852: Part 2:1982 (Schedule 1: Part 1) Crib 5 test	< 60 g

Standard colour is white.

The Vita Group reserves the right to update product data information without prior notice.

Issued 01/2021.