



## Awning Cover Fabric Technical Information

### Fabric Type

|                |                          |
|----------------|--------------------------|
| Name of Fabric | Advaning Awning Cover    |
| Base Fabric    | 600D Polyester (290g/m2) |
| Coating        | TPE                      |

### Water Pressure

| Test                 | Test Result                | Testing Lab | Testing Method     |
|----------------------|----------------------------|-------------|--------------------|
| Hydrostatic Pressure | Up to 4.44 psi (3124.70mm) | Intertek    | AATCC-127 Method B |

### Chemical PVC

| Test             | Test Result   | Testing Lab | Testing Method      |
|------------------|---------------|-------------|---------------------|
| PVC (LOD 10 ppm) | None Detected | ATS         | ASTM D3452-06(2012) |

### Heavy Metals

| Test     | Test Result   | Testing Lab | Testing Method |
|----------|---------------|-------------|----------------|
| Lead     | None Detected | ATS         | ASTM 1479-6    |
| Cadmium  |               |             |                |
| Chromium |               |             |                |
| Mercury  |               |             |                |

### Phthalates

| Test  | Test Result   | Testing Lab | Testing Method     | Test | Test Result   | Testing Lab | Testing Method     |
|-------|---------------|-------------|--------------------|------|---------------|-------------|--------------------|
| DPENP | None Detected | ATS         | CPSC-CH-C1001-09.3 | DnBP | None Detected | ATS         | CPSC-CH-C1001-09.3 |
| DHEXP |               |             |                    | BBP  |               |             |                    |
| DCHP  |               |             |                    | DINP |               |             |                    |
| DIBP  |               |             |                    | DIDP |               |             |                    |
| DEHP  |               |             |                    | DnOP |               |             |                    |

\*The complete report is available upon request