



# DATA SHEET / SPECIFICATION

## CH 2715

### Description:

Combustion modified polyurethane foam.

CH 2715		
Property	Test Procedure	CH 2715
Relative Net Density	ISO 845	25-28 kg/m <sup>3</sup>
Hardness ILD (40%)	ISO 2439	70-100 N
SAG Factor	ISO 2439	Min 2.5
Compression Set (50% 22h 70°C)	ISO 1856	Max 10%
Resilience	ISO 8307	Min 48%
Tensile Strength	ISO 1798	Min 50 kPa
Elongation at Break	ISO 1798	Min 85%
Flammability	BS 5852: Part 2:1982 (Schedule 1: Part 1) Crib 5 test	< 60g

Standard colour is grey-blue.

The Vita Group reserves the right to update product data information without prior notice.

Issued 01/2021.

