

Total Lead (Pb) Content in Surface Coating (U.S. 16 CFR Part 1303 and CPSIA Section 101)

As per Standard Operating Procedure for Determining Lead (Pb) in paint and other similar surface coatings, test method CPSC-CH-E1003-09.1 was used and total Lead content was determined by Inductively Coupled Plasma - Optical Emission Spectrometry.

<u>Element</u>	<u>Result (ppm) θ</u>	<u>Reporting Limit (ppm)</u>	<u>Limit (ppm)</u>
	<u>Tested Component</u>		
	<u>(1+2) (9)</u>		
Lead (Pb)	ND	10	90

The above limit was quoted according to U.S. CFR Title 16 Part 1303 and U.S. Consumer Product Safety Improvement Act 2008 Title I, Section 101 for total Lead content in surface coating.

ppm = parts per million = mg/kg

ND = Not detected (less than reporting limit)

θ = Single result for each test component/group

Tested components: See component list in the last section of this report